

Custom Foils Company
 185 Foundry St.
 Newark, N.J. 07105
 Tel: 973-344-1434 Fax: 973-589-1617
 www.customfoilscompany.com

November 30, 2011

RE: REACH: Substances of Very High Concern (SVHC)
 Dear Valued Customer:

Concerning our P, E, D, K, H, A, M, W, and EW series pigments manufactured after 1991, to the best of our knowledge, based upon the information provided by our raw material suppliers, we do not believe that the following chemicals are present:

Chemical Substance	Cas. No.
2,4-Dinitrotoluene	121-14-2
2-Ethoxyethanol	110-80-5
2-Methoxyethanol	109-86-4
4,4'- Diaminodiphenylmethane (MDA)	101-77-9
5-tert-butyl-2,4,6-trinitro-m-xylene (musk xylene)	81-15-2
Acrylamide	79-06-1
Alkanes, C10-13, chloro (Short Chain Chlorinated Paraffins)	5 85535-84-8
Aluminosilicate Refractory Ceramic Fibres are fibres covered by index number 650-017-00-8 in Annex VI, part 3, table 3.2 of Regulation (EC) No 1272/2008 of the European Parliament and of the Council of 16 December 2008 on classification, labelling and packaging of substances and mixtures, and fulfil the two following conditions: a) Al ₂ O ₃ and SiO ₂ are present within the following concentration ranges: Al ₂ O ₃ : 43.5 – 47 % w/w, and SiO ₂ : 49.5 – 53.5 % w/w, or Al ₂ O ₃ : 45.5 – 50.5 % w/w, and SiO ₂ : 48.5 – 54 % w/w, b) fibres have a length weighted geometric mean diameter less two standard geometric errors of 6 or less micrometres (µm).	Extracted from Index no.: 650-017-00-8
Ammonium dichromate	7789-09-5
Anthracene	120-12-7
Anthracene oil	90640-80-5
Anthracene oil, anthracene paste	90640-81-6
Anthracene oil, anthracene paste, anthracene fraction	91995-15-2
Anthracene oil, anthracene paste, distn. lights	91995-17-4
Anthracene oil, anthracene-low	90640-82-7
Benzyl butyl phthalate (BBP)	85-68-7
Bis (2-ethylhexyl)phthalate (DEHP)	117-81-7
Bis(tributyltin)oxide (TBTO)	56-35-9
Boric acid	10043-35-3 / 11113-50-1
Chromic acid, Oligomers of chromic acid and dichromic acid, Dichromic acid	7738-94-5 13530-68-2
Chromium trioxide	1333-82-0
Cobalt dichloride	7646-79-9
Cobalt(II) carbonate	513-79-1
Cobalt(II) diacetate	71-48-7
Cobalt(II) dinitrate	10141-05-6
Cobalt(II) sulphate	10124-43-3
Diarsenic pentaoxide	1303-28-2
Diarsenic trioxide	1327-53-3
Dibutyl phthalate (DBP)	84-74-2
Diisobutyl phthalate	84-69-5

Custom Foils Company
 185 Foundry St.
 Newark, N.J. 07105
 Tel: 973-344-1434 Fax: 973-589-1617
 www.customfoilscompany.com

Disodium tetraborate, anhydrous	1303-96-4/ 1330-43-4/ 12179-04-3
Hexabromocyclododecane (HBCDD) and all major diastereoisomers identified: Alpha-hexabromocyclododecane Beta-hexabromocyclododecane Gamma-hexabromocyclododecane	(134237-50-6) (134237-51-7) (134237-52-8)
Lead chromate	7758-97-6
Lead chromate molybdate sulphate red (C.I. Pigment Red 104)	12656-85-8
Lead hydrogen arsenate	7784-40-9
Lead sulfochromate yellow (C.I. Pigment Yellow 34)	1344-37-2
Pitch, coal tar, high temp.	65996-93-2
Potassium chromate	7789-00-6
Potassium dichromate	7778-50-9
Sodium chromate	7775-11-3
Sodium dichromate	7789-12-0/ 10588-01-9
Tetraboron disodium heptaoxide, hydrate	12267-73-1
Trichloroethylene	79-01-6
Triethyl arsenate	15606-95-8
Tris(2-chloroethyl)phosphate	115-96-8
Zirconia Aluminosilicate Refractory Ceramic Fibres are fibres covered by index number 650-017-00-8 in Annex VI, part 3, table 3.2 of Regulation (EC) No 1272/2008 of the European Parliament and of the Council of 16 December 2008 on classification, labelling and packaging of substances and mixtures, and fulfil the two following conditions: a) Al ₂ O ₃ , SiO ₂ and ZrO ₂ are present within the following concentration ranges: Al ₂ O ₃ : 35 – 36 % w/w, and SiO ₂ : 47.5 – 50 % w/w, and ZrO ₂ : 15 - 17 % w/w, b) fibres have a length weighted geometric mean diameter less two standard geometric errors of 6 or less micrometres (µm).	Extracted from Index no.650-017-00-8

Any trace quantities may exist as impurities in our raw materials. A substantial number of our raw material suppliers, as well as in prior succession, further upstream raw material suppliers, may not routinely test for the presence of these. Additionally, any of our raw material suppliers may at a future time, provide other information to alter this statement. None of these chemicals are deliberately added as a raw material component to our products. Custom Foils Company does not routinely test for the presence of these.

Sincerely,
 Baldwin Chan